

Odlévání

Silikon	Tvrdost
Lukopren N 8100	22 °ShA
Lukopren N 8200	24 °ShA
Lukopren N 5221	23 - 25 °ShA
Lukopren N Super	30 - 32 °ShA
Lukopren N 1522	53 - 55 °ShA
Lukopren N 5541	55 - 57 °ShA
Lukopren N 1725	58 - 60 °ShA
Lukopren N 6681	59 - 63 °ShA - silentblok liberty??
Polyuretan	Tvrdost
GAFORM E70	70 Shore A (+-4)
GAFORM E45	45 Shore A (+-5)

From:

<https://wiki.spoje.net/> - **SPOJE.NET**

Permanent link:

https://wiki.spoje.net/doku.php/howto/mechanical_engineering/casting

Last update: **2021/05/01 21:07**

